

Listing of Amended Claims

1. (Currently Amended) A composition comprising
 - (1) 30 to 98.5 weight percent highly crystalline polypropylene base resin having a tacticity index greater than 90 and melt flow rate from 0.5 to 100 g/10 min.;
 - (2) 1 to 70 weight percent ~~dispersed component selected from the group consisting of filler type materials and~~ polymers which ~~are~~ is incompatible with said base resin selected from the group consisting of ethylene-vinyl alcohol copolymer, polyamide, polyester, polyvinylchloride, polyvinylidenedichloride, ethylene-carbon monoxide copolymer and terpolymer, polycarbonate, polyether, high impact polystyrene, styrene-acrylonitrile copolymer and acrylonitrile-butadiene-styrene terpolymer; and
 - (3) 0.25 to 10 weight percent grafted propylene-ethylene impact copolymer ~~grafted with a carboxylic acid or derivative which is a reactor-made intimate mixture of propylene homopolymer and 20 weight percent or more propylene-ethylene copolymer grafted with 1 weight percent or more maleic anhydride.~~
2. (Cancelled)
3. (Currently Amended) The composition of Claim 2 1 wherein the tacticity index is greater than 94 and melt flow rate is from 2 to 50 g/10 min.
4. (Cancelled)
5. (Currently Amended) The composition of Claim 4 1 wherein the propylene-ethylene impact copolymer has an ethylene content from 5 to 30 percent and molecular weight distribution of 7 or less.
6. (Currently Amended) The composition of Claim 4 5 wherein ~~the graft monomer is maleic anhydride,~~ the graft monomer content is 1.75 to 3.5 weight percent and the graft to melt flow rate ratio of the grafted impact copolymer is 0.5 or above.

7. (Currently Amended) The composition of Claim 1 comprising 50 to 95 weight percent polypropylene base resin, 2.5 to 60 weight percent incompatible polymer ~~dispersed component~~ and 0.5 to 5 weight percent grafted propylene-ethylene impact copolymer.
8. (Cancelled)
9. (Currently Amended) The composition of Claim 8 ~~1~~ wherein the incompatible polymer ~~dispersed component~~ is a polyamide selected from the group consisting of polytetramethylene adipamide, polyhexamethylene adipamide, polyhexamethylene azelamide, polyhexamethylene sebacamide, polyhexamethylene dodecanoamide, polycaprolactam, polybutyrolactam, polypivalolactam and poly-11-aminoundecanoic acid.
10. (Cancelled)
11. (Currently Amended) The composition of Claim ~~10~~ 9 comprising 50 to 95 weight percent polypropylene base resin, 1 to 30 weight percent ~~dispersed component~~ polyamide and 0.5 to 5 weight percent grafted propylene-ethylene impact copolymer.
12. (Cancelled)
13. (Cancelled)
14. (Cancelled)
15. (Cancelled)
16. (Cancelled)
17. (Cancelled)
18. (Cancelled)
19. (Cancelled)
20. (New) The composition of Claim 11 wherein the polyamide is polycaprolactam.